

D E
D
A R

PATCHWORK | DEDAR



COMPOSITION

60% PES FR TREVIRA
40% PES FR

**COLOUR FASTNESS
TO LIGHT**

Note 6-7
EN ISO 105-B02

PILLING

Note 3-4 @ 5000 rubs
ISO 12945

MARTINDALE



11.000 rubs
UNI ENI ISO 12947-2

CARE




NOTES


Slight differences in colour may occur




010



012




014




011




004




005




006



007



008



013

PROUST | DEDAR



COMPOSITION

100% PES

COLOUR FASTNESS

TO LIGHT

Note 3-4

EN ISO 105-B02

PILLING

Note 5 @ 5.000 rubs


ISO 12945

MARTINDALE

40.000 rubs



UNI ENI ISO 12947-2

CARE



NOTES

Slight differences in colour may occur



bolzan